



ZIBO HOLY MASTERBATCH CO.,LTD

Tel: 0086-0533-2293766 Fax: 0086-0533-2293765 Email: sales@zbholy.com Web: www.zbholy.com

Add: Eastern chemical zone, Zhangdian, Zibo, Shandong, China

Product Information and Data Sheet

Product Name: CaO Desiccant Masterbatch

Physical Property

Items	Result	Unit
CaO Powder content	80	Wt%
Melt Temperature	120~150	°C
Bulk Density	1.3~1.5	g/cm ³
Particle size of CaO	1000	mesh
Water Absorption	≤ 20	Wt%
Time to keep (after mix)	< 48	Hours

Properties:

Appearance(Surface color)	: White
Composition	: Additives, CaO, Carrier resin
Processing temperature	: 140-280°C
Usagerate	: 3~10%
Pallet Size	: 5x3(±0.3)mm
Carrier resin	: PE
Compatibility	: PE/PP etc.
Packing	: 2.5kg/5kg per bag
Storage	: Keep at dry condition

Caution:

This product information is based on our generate and dose not constitute a specification. Since many factors affect the use of our products, no warranty is given or implied with respect to this information or patent infringement. We do not accept liability for any loss or damage arising from the use of this information. All sales are subject to our standard terms and condition of sale.