

PRODUCT NAME: CaCO3 masterbatch			
SUITABLE PRODUCT FOR: Injection molding, Film blowing, Extrusion molding etc.			
SUGGESTED ADD RATIO: Recommend to add 5~50%			
OBSERVATION: The masterbatch dosage is according to the final product requirements.			
S/ N	PROPERTIES	STANDARD	RANGE
1	CARRIER RESIN	/	PE/PP
2	BRAND	/	HOLY
3	ORIGIN	/	SHANDONG,CHINA
4	PELLET SHAPE & SIZE	/	5x3(±0.3)mm
5	COLOR	/	WHITE
6	POLYMER	CAS NO.	9002-88-4
7	ADDITIVE	CAS NO.	110-30-5
8	CaCO3 Powder Size	/	600~1500mesh
9	CaCO3 content	/	75%~85%
10	MELT TEMPERATURE	ISO11357:1999	140℃
11	MOISTURE CONTENT	ASTM D 789	≤0.15%
12	MFI 190℃/2.16KGS	ASTM D 1238	1-15 g/10min
13	DENSITY	ASTM D 792	1.6-1.7g/cm3
14	PACKAGE	/	25kg per PP woven bag, or customized
15	PAYMENT TERMS	/	TT,LC,etc.
16	DELIVERY TIME	/	Less than 7 days
17	MOQ	/	1 Tons
18	STORAGE	Keep the products in a dry, ventilated place, Note to avoid moisture and insolation, rain and breakage in transportation.	

ZIBO HOLY MASTERBATCH CO.,LTD

Tel: 0086-0533-2293766 Fax: 0086-0533-2293765 Web: www.zbholy.com

Add: Eastern chemical zone, Zhangdian, Zibo, Shandong, China